



The genus *Abies* (True Firs) is composed of about 40 species native to North America [9], Central America [7], Africa [2], Europe [1] and Eurasia [25]. There are two recognized varieties of this species, the typical Subalpine Fir [*Abies lasiocarpa* (Hook.) Nutt. var. *lasiocarpa*] and Corkbark Fir [*Abies lasiocarpa* var. *arizonica* (Merriam) Lemm.]. *Abies* is the classical Latin name of silver fir (*Abies alba* Mill.) of Europe. The word *lasiocarpa* means with woolly or hairy fruits.

Other Common Names: Abete bianco americano, abete sughero, abeto blanco americano, abeto corcho, alpen-den, alpine fir, amerikansk vit-gran, Arizona cork fir, Arizona corkbark fir, Arizona fir, balsam, balsam fir, berg-gran, black balsam, caribou fir, cork fir, corkbark, corkbark fir, downey-cone fir, downy-cone subalpine fir, kork-gran, kurkschors-den, mountain balsam, mountain fir, Oregon balsam fir, Oregon balsam-tree, pino real blanco, pino real blanco de las, pumpkin-tree, Rocky Mountain fir, Rocky Mountains fir, sapin blanc d'Amerique, sapin concolore, sapin d'Arizona, sapin liege, subalfir, **subalpine fir**, western balsam, western balsam fir, white balsam, white fir.

Distribution: Subalpine Fir grows naturally in mountains from central Yukon and the eastern parts of southeast Alaska south through Alberta and British Columbia. Also, from Washington, Oregon, Idaho and western Montana south to central Colorado southern New Mexico and southeast Arizona. It also grows locally in northeast Nevada and northwest California.

The Tree: Subalpine Fir attains heights of 130 feet, with diameters of 3 feet. It grows from near sea level in the northern limits of its range to 12,000 feet in the south.

General Wood Characteristics: The wood ranges from tan to brown with shades of red or pink. The sapwood is not clearly differentiated from the heartwood. It has a medium luster and has no distinctive odor or taste. It varies from very light, soft and weak to moderately heavy, hard and strong. It is easy to work, but poorly resistant to decay,

Mechanical Properties (2-inch standard)

	Specific gravity	MOE x10 ⁶ lbf/in ²	MOR lbf/in ²	Compression		WML ^a in-lbf/in ³	Hardness lbf	Shear lbf/in ²
				Parallel lbf/in ²	Perpendicular lbf/in ²			
Green	0.31	1.05	4900	2300	190	4.4	260	700
Dry	0.32	1.29	8600	4860	390	2.9	350	1070

^aWML = Work to maximum load.
Reference (56, 192)..

Drying and Shrinkage

Type of shrinkage	Percentage of shrinkage (green to final moisture content)		
	0% MC	6% MC	20% MC
Tangential	7.4	NA	NA
Radial	2.6	NA	NA
Volumetric	9.4	NA	NA

References: (56, 185).

Kiln Drying Schedules^a

Conventional temperature/moisture content-controlled schedules^a

Condition	4/4, 5/4 stock	6/4 stock	8/4 stock	10/4 stock	12/4 stock	British schedule 4/4 stock
Standard	T12-B5	NA	T12-B4	NA	NA	NA

^aReference (28, 185).

Conventional temperature/time-controlled schedules^a

Condition	Lower grades			Upper grades			
	4/4, 5/4 stock	6/4 stock	8/4 stock	4/4, 5/4 stock	6/4 stock	8/4 stock	12/4, 16/4 stock
Standard	291	291	291	294	294	294	288

^aReferences (28, 185).

High temperature^a

Condition	4/4, 5/4 stock	6/4 stock	8/4 stock	Other products
Standard	400	400	400/ 416	NA

^aReferences (28, 184).

Working Properties: It is reported to work well.

Durability: Heartwood rated as slightly or nonresistant to decay.

Preservation: No information available at this time.

Uses: Building construction, boxes, crates, planing mill products, sashes, doors, frames, food containers and pulpwood.

Toxicity: May cause dermatitis or eczema (3,7&12).

Additional Reading and References Cited (in parentheses)

- Alexander, R. R.; Shearer, R. C., and Shepperd, W. D. *Abies lasiocarpa* (Hook.) Nutt., Subalpine Fir. in: Burns, R. M. and Honkala, B. H., tech. coords. Silvics of North America. Volume 1, Conifers. Washington, DC: USDA Forest Service; 1990; pp. 60-70.
- Boone, R. S.; Kozlik, C. J.; Bois, P. J., and Wengert, E. M. Dry kiln schedules for commercial woods - temperate and tropical. Madison, WI: USDA Forest Service, FPL-GTR-57; 1988.
- Hausen, B. M. Woods injurious to human health. A manual. New York, NY: Walter de Gruyter; 1981.
- Hyam, R. and Pankhurst, R. Plant and their names. A concise dictionary. Oxford, UK: Oxford University Press; 1995.
- Little, jr. E. L. Checklist of United States trees (native and naturalized). Washington, DC: USGPO, USDA Forest Service, Ag. Handbook No. 541; 1979.
- Markstrom, D. C. and McElderry, S. E. White Fir, An American Wood. Washington, DC, USA: USDA Forest Service, FS-237; 1984.
- Mitchell, J. and Rook, A. Botanical dermatology: plants and plant products injurious to the skin. Vancouver, BC: Greenglass Ltd.; 1979.
- Record, S. J. and Hess R. W. Timbers of the new world. New Haven, CT: Yale University Press; 1943.
- Simpson, W. T. Dry kiln operator's manual. Madison, WI: USDA Forest Service, FPL Ag. Handbook No. 188; 1991.
- Summitt, R. and Sliker, A. CRC handbook of materials science. Vol. 4. Boca Raton, FL: CRC Press, Inc.; 1980.
- USDA. Wood handbook: wood as an engineering material. Madison, WI: USDA Forest Service, FPL Ag. Handbook No. 72; 1974.
- Woods, B. and Calnan, C. D. Toxic woods. British Journal of Dermatology. 1976; 95(13):1-